

## OVERVIEW

**Terraroc PMR is a high strength structural repair mortar which is suitable for use for repairing all types of concrete. Terraroc PMR is polymer modified to ensure excellent adhesion. Terraroc PMR is shrinkage compensated and is suitable for repairs up to 50mm on vertical surfaces and 30mm on overhead situations. Terraroc PMR is suitable for spray application.**

## PROPERTIES

Terraroc PMR is a pre-mixed blend of special cements, plasticizers, polymers and shrinkage compensating additives with the following properties:

- Ready to use
- Shrinkage compensated
- Factory controlled mix design
- Extra high strength
- Excellent adhesion

## AREAS OF USE

Terraroc PMR is designed for use as part of the Terraco concrete repair system and is recommended for high-build repair work up to 50mm vertically and 30mm overhead, in a single application.

## PREPARATION OF SURFACE

Do not apply at temperatures below 5°C. Remove all defective concrete back to the reinforcements, treat reinforcements with Epiprime ZR (see separate data sheet). Avoid feather edging. The repair area should be a minimum depth of 10mm. Thoroughly wet the surface with water and apply a coat of Terrabond A by scrubbing it well into the surface. Allow it to become tacky before applying the Terraroc PMR.

## MIXING

Ensure that the mixing water is constant for each bag of compound (3.75ltr water/25kg Terraroc PMR). A mechanical mixer is necessary to ensure consistency of the final mix. Add the powder to the water and mix continuously for 3 to 5 minutes.

## APPLICATION & CLEANING OF TOOLS

Apply to the prepared substrate by trowel ensuring that it is well compacted onto the primed surface/reinforcements. Build up in layers until the desired thickness is achieved. Where very thick sections are required allow the initial layer of Terraroc PMR to set, scratch the surface to provide a mechanical key and prime with Terrabond A before applying the final layer of Terraroc PMR. Finish using a steel float. Terraroc PMR should not be applied in layers less than 10mm.

Clean tools and equipment with water after use.

## CURING

Terraroc PMR should be cured immediately after troweling is finished by applying Terrabond A to the surface. In harsh conditions the supplementary use of hessian or polythene must be used to ensure proper curing.

## HEALTH & SAFETY

Avoid prolonged contact with eyes and skin. For detailed information refer to relevant material safety data sheet.

## PACKAGING & STORAGE

Terraroc PMR is packed in 25kg valve craft bags.

Terraroc PMR should be stored in a clean dry area protected from direct sunlight and extreme heat and cold. The pallets can be stacked two high provided care is taken. Opened sacks should be used first. Unopened sacks can be stored for 6 months. Use oldest material first.

TERRACO offers a comprehensive range of products and services for most concrete and finishing needs. Please contact the TERRACO Technical Service Department or your local TERRACO agent for further information, samples, demonstrations and instructor services. The information given in this leaflet is based upon laboratory research, as well as extensive field work and application. All products are sold subject to standard conditions of sale which are available on request. This information is based on TERRACO's present state of knowledge and is intended to provide general information on TERRACO's products and their methods of use. The prospective user is recommended to determine the suitability of TERRACO's suggestions and products before adopting them on a commercial scale.

## TECHNICAL DATA

<b>Product</b>	High strength structural repair mortar.
<b>Binder</b>	Hydraulic/organic.
<b>Colours</b>	Grey.
<b>Compressive Strength</b>	45 N/mm <sup>2</sup> (7 days), 55 N/mm <sup>2</sup> (28 days).
<b>Flexural Strength</b>	10 N/mm <sup>2</sup> (28 days).
<b>Tensile Adhesion</b>	1.62 N/mm <sup>2</sup> Con A 1.64 N/mm <sup>2</sup> Con B 2.00 N/mm <sup>2</sup> Con C
<b>Set Time</b>	3 hours (initial), 5 hours (final).
<b>Wet Density</b>	2000 kg/m <sup>3</sup>
<b>Water Demand</b>	15% (3.75 ltr water/25kg bag).
<b>Application Thickness</b>	50mm (vertical), 30mm (overhead).
<b>Yield</b>	25kg of powder + 4.5ltr of water gives 14ltr mix.
<b>Consumption Rate</b>	1.9kg/m <sup>2</sup> /mm thickness
<b>Packaging</b>	25kg valve craft bags.
<b>Storage</b>	6 months in original unopened container.

For technical enquiries please contact your nearest Terraco representative:

### CHINA:

**Terraco Architectural Coatings China Co., Ltd.**  
Tel: +86 (0)20 8759 4742  
Fax: +86 (0)20 8526 8056  
E-mail: sales@terraco.com.cn  
Web: www.terraco.com.cn

**Terraco Chemical (Shanghai) Co., Ltd.**  
Tel: +86 (0)21 621020 48 / 18  
Fax: +86 (0)21 625205 47  
Email: sales@terraco.com.cn  
Web: www.terraco.com.cn

### EGYPT:

**Terraco Egypt Chemical Industries S.A.E.**  
Tel: +20 (0)22 29184 53 / 57 / 58  
Fax: +20 (0)22 29184 80  
E-mail: terraco@terraco.com.eg  
Web: www.terraco.com.eg

### JORDAN:

**Jordan Swedish Polymers Industrial Corp.**  
Tel: +962 (0)6 553 8751  
Fax: +962 (0)6 553 6560  
E-mail: terraco@nol.com.jo  
Web: www.terraco.jo

### IRELAND:

**Terraco Technical Centre, Ireland**  
Tel: +353 (0) 404 66555  
Fax: +353 (0) 404 66654  
E-mail: technical-centre@terraco.com  
Web: www.terraco.com

### PAKISTAN:

**Terraco Pakistan Pvt. Ltd.**  
Tel: +92 (0)42 3529 70 56-8  
Fax: +92 (0)42 3529 70 55  
Email: terraco@terraco.pk  
Web: www.terraco.com

### ROMANIA:

**Terraco Romania SRL**  
Tel: +40 (0)749 203 133  
Fax: +40 (0)318 148 810  
E-mail: ahaque@terraco.com  
Web: www.terraco.com

### RUSSIA:

**OOO Terraco Sweden Ltd, Russia**  
Tel: +7 (0)495 9212 237  
Fax: +7 (0)495 6273 881  
E-mail: adm@terraco.ru  
Web: www.terraco.ru

### OOO Terraco Vostok Ltd

Tel: +7 (0)4212 410563  
Fax: +7 (0)4212 410591  
E-mail: terracovostok@terraco.khn.ru  
Web: www.terraco.com

### SOUTH KOREA:

**Terraco Korea Co., Ltd**  
Tel: +82 (0) 2 5611 551  
Fax: +82 (0)2 5671 771  
E-mail: terraco@terraco.co.kr  
Web: www.terraco.co.kr

### THAILAND:

**Terraco Industry (Thailand) Limited**  
Tel: +66 (0)2 946 68 56 / 58  
Fax: +66 (0)2 946 68 59  
E-mail: terraco@terraco.co.th  
Web: www.terraco.com

### TURKEY:

**Terraco Yapi Malzemeleri Sanayi Ve Ticaret AS**  
Tel: +90 (0)222 236 0423  
Fax: +90 (0)222 236 0425  
E-mail: terraco@terraco.com.tr  
Web: www.terraco.com.tr

### UAE:

**Terraco UAE Ltd**  
Tel: +971 (0)4 326 2699  
Fax: +971 (0)4 326 2733  
E-mail: terraco@terraco.ae  
Web: www.terraco.com

### UK:

**ADDAGRIP**  
Tel: +44 (0)1825 761 333  
Fax: +44 (0)1825 768 566  
E-mail: sales@addagrip.co.uk  
Web: www.addagrip.co.uk / www.terraco.com

### VIETNAM:

**Terraco Vietnam Co., Ltd**  
Tel: +84 (0)650 3 820 100  
Fax: +84 (0)650 3 820101  
E-mail: terraco@terraco.com.vn  
Web: www.terraco.com